	Painting top of roofs with bitumen of approved quality at 17kg per 10 sqm impregnated with a coat of coarse sand at 60 cudm per 10sqm including cleaning the slab surface with brushes and finally with a piece of cloth lightly soaked in kerosene oil complete with residual type petroleum bitumen of penetration 80/100	Sqm	25
11.5	10 cm thick (average) mud phaska of damped brick earth on roofs laid to slope consolidated and plastered with 25mm thick mud mortar mixed with bhusa at 35 kg per cum of earth and gobri leaping with mix 1:1 (1 clay: 1 coy dung) and covered with flat tile bricks of class designation 100 grouted with cement mortar 1:3 (1 cement : 3 fine sand) mixed with 2% of integral water proofing compound by weight of cement and finished neat with F.P.S. brick tiles	Sqm	25